



Mixing ratio for Houseliner SLOW , MEDIUM and FAST

Weight in KG	Base in GRAMS	Hardener in GRAMS
1	714	286
2	1429	571
3	2143	857
4	2857	1143
5	3571	1429
6	4286	1714
7	5000	2000
8	5714	2286
9	6429	2571
10	7143	2857
11	7857	3143
12	8571	3429
13	9286	3714
14	10000	4000
15	10714	4286
16	11429	4571
17	12143	4857
18	12857	5143
19	13571	5429
20	14286	5714
21	15000	6000
22	15714	6286
23	16429	6571
24	17143	6857
25	17857	7143
26	18571	7429
27	19286	7714
28	20000	8000
29	20714	8286



Mixing ratio for Houseliner HOT CURE

Weight in KG	Base in GRAMS	Hardener in GRAMS
1	794	206
2	1587	413
3	2381	619
4	3175	825
5	3968	1032
6	4762	1238
7	5556	1444
8	6349	1651
9	7143	1857
10	7937	2063
11	8730	2270
12	9524	2476
13	10317	2683
14	11111	2889
15	11905	3095
16	12698	3302
17	13492	3508
18	14286	3714
19	15079	3921
20	15873	4127
21	16667	4333
22	17460	4540
23	18254	4746
24	19048	4952
25	19841	5159
26	20635	5365
27	21429	5571
28	22222	5778
29	23016	5984